

DESCRIPTION

Total thickness	EN 428	mm	2.15
Thickness of wearlayer	EN 429	mm	0.70
Weight	EN 430	g/m ²	2805
Width of sheet	EN 426	cm	200
Length of sheet	EN 426	lm	25

CLASSIFICATION

Norm / Product specification	-	-	EN 649
European classification	EN 685	class	34 - 43
Fire rating	EN 13 501-1	class	B _{fl} -s1
Static electrical propensity	EN 1815	kV	< 2
Slip resistance wet : ramp test with oil	DIN 51 130	class	R10

PERFORMANCE

Wear resistance	EN 660-2	mm ³	≤ 2.0
Wear group	EN 649	-	T
Dimensional stability	EN 434	%	≤ 0.40
Residual indentation (exigency)	EN 433	mm	≤ 0.10
Residual indentation (measure)	-	mm	~ 0.03
Thermal conductivity	EN 12 524	W/(m.K)	0.25
Colour fastness	EN 20 105 - B02	degree	≥ 6
Chemical products resistance	EN 423	-	OK
Anti-bacterial and fungicidal treatment	-	-	Sanosol®
Surface treatment	-	-	Protecsol®

CE MARKING

	EN 14041	-	  
		-	